

# Sanafarbe Marble Finishing

breathable Mineral coating with marmorino (lime and marble powder) effect



Thick coating-finishing, easy to spread, in imitation of marble, which can be obtained in glossy or matte form, for external and internal use, breathable and water-repellent, based on lime putty, micronised marble dust and specific agents, mould-proof, non-absorbent vis-à-vis soiling. Available in various colours, with ample alternative shades, which can be formulated on request.

**CUSTOMS CODE:** 3209 9000

**COMPONENTS:** Single-component

**APPEARANCE:** Paste

**AVAILABLE COLORS:** Request available colors

**PACKAGING AND DIMENSIONS:** Pail 20 kg

## FEATURES AND BENEFITS

The long hardening lime putty, used as a binder, confers distinct breathable, antiseptic and anti-mildew properties. The high polishing aptitude with the spatula exalts, the aesthetic, repellent and anti-fouling properties. The special formula of SANAFARBE MARMORINO FINITURA, based on long hardening lime putty, micronised marble dust, natural pigments and minerals, gives great breathability to the coating, remarkable mildewcide and antibacterial properties.

## FIELDS OF APPLICATION

Decorative final coat, with marmorino (lime and marble powder) effect, for the construction of fine protective and decorative coatings, for ecological building interventions, new buildings and in the restoration of vintage buildings and monuments.

## ALLOWED SUPPORTS

Plasters - Paint

## PREPARATION OF SUPPORTS

Application surfaces should be clean, free of soiling, crumbling and non-adhering parts, dust, etc., conveniently saturated with water until they reach the condition "saturated with dry surface".



## MODE OF USE

SANAFARBE "MARMORINO" is ready-to-use, in the form of a thixotropic paste and must be applied with stainless steel trowel, and in two or three coats, depending on the desired level coverage. The last coat must be trowelled carefully, always with a spatula or stainless steel trowel, when the product begins to dry. SANAFARBE "MARMORINO" can be applied to internal and external surfaces. In the case of cement plaster or lime, like in pre-existing lime-based paints, as long as they are compact and not crumbly, apply directly. Any organic type paints (washable, solvent, etc.) should be removed. In the presence of rough and/or non-homogeneous surfaces, preliminary homogenisation by application of SANAFARBE MARMORINO FONDO is required.

## APPLICATION METHODS

Spatula

## TOOL CLEANING

Water

## KEY FEATURES



Density: 1.48 kg/dm<sup>3</sup>



Shelf-life: 12 months



Temperature of use: +8 / +30 °C



To be applied in two coats

## TECHNICAL SPECIFICATIONS

a 20°C

Complete hardening at 20°C **12 - 24 h**

a 20°C

Touch hardening at 20°C **4 h**

## CONSUMPTION

Approximately 0,6 kg of SANAFARBE MARMORINO FINITURA for each square metre of surface to be covered.

## STORAGE AND CONSERVATION

Protect from freezing. Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity.



## ADDITIONAL CONTENT



## WARNINGS AND PRECAUTIONS

Avoid prolonged direct exposure of the fresh surfaces to the wind and the sunshine. The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge.

Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage.

Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: [www.azichem.com](http://www.azichem.com). The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: [www.azichem.com](http://www.azichem.com).

It is forbidden to dispose of the product and/or packaging in the environment.

