

# Syntech Drainpur



**CUSTOMS CODE:**

**COMPONENTS:** Two-components

**APPEARANCE:** Liquid + Liquid

**AVAILABLE COLORS:** Transparent

**PACKAGING AND DIMENSIONS:** Can 1 kg [A] - Can 1 kg [B] - Kit: 1 Can 1 kg [A] + 1 Can 1 kg [B]

## ALLOWED SUPPORTS

Concrete


## APPLICATION METHODS


To be added to other components


## TOOL CLEANING


Syntech Diluente Poliuretano


## KEY FEATURES

 Density: 1.15 ± 0.05 kg/l

 Use wearing protective glasses

 UV-resistant

 Shelf-life: 12 months

 Use wearing protective gloves



## TECHNICAL SPECIFICATIONS

Touch hardening at 20°C **4-6 h**

EN 1015-6

Density **1800 kg/m<sup>3</sup>**

EN 13892-

Compressive strength  $\geq$  **20 N/mm<sup>2</sup>**

EN 13892-8

Classe **B1.5**  $\geq$  **1.5 N/mm<sup>2</sup>**

EN ISO 6272

Impact resistance Classe **IR4**  $\geq$  **4 N/mm<sup>2</sup>**

Brookfield ASTM D 2196

Viscosity **2000  $\pm$  100 mPas**

Complete hardening at 20°C **7 day**

Dry residue **99.5  $\pm$  0.05 %**

EN 13892-

Flexural strength  $\geq$  **5 N/mm<sup>2</sup>**

EN 13501-1

Fire resistance Classe **F**

Working temperature **-20/+70 °C**

## STORAGE AND CONSERVATION

Protect from freezing. Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Store the product at a temperature between +10°C and +30°C.

## WARNINGS AND PRECAUTIONS

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge. Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage. Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: [www.azichem.com](http://www.azichem.com). The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: [www.azichem.com](http://www.azichem.com). It is forbidden to dispose of the product and/or packaging in the environment.

