

Syntech Pavicrom Fast



CUSTOMS CODE: 3907 3000

COMPONENTS: Two-components

APPEARANCE: Liquid + Liquid

AVAILABLE COLORS: RAL classic

PACKAGING AND DIMENSIONS: Pail 2.5 kg [A] - Pail 5 kg [A] - Pail 2.5 kg [B] - Pail 5 kg [B] -
Kit: 1 Pail 2.5 kg [A] + 1 Pail 2.5 kg [B] - Kit: 1 Pail 5 kg [A] + 1 Pail 5 kg [B]

OBTAINED CERTIFICATIONS AND REGULATIONS



ALLOWED SUPPORTS

Concrete - Resin coatings

APPLICATION METHODS





Low pressure airless nebulizer - Brush - Paint roller





TOOL CLEANING

Water



KEY FEATURES

- A:B** Mixing ratio: 1:1 _
 Pot-life: 50-70 min
 Solvent-free
 To be applied in two coats
 Use wearing protective gloves

-  Nonflammable
 Shelf-life: 12 months
 Temperature of use: +10 / +35 °C
 Use wearing protective glasses

TECHNICAL SPECIFICATIONS

EN 2812-1
Resistance to particular washing agents (detergent D) **NO ALTERATION**

Time before second coat at 20°C **4 - 48 h**

EN 1542
> **3.5 N/mm²**

EN 1198
Resistance to washing **Ldft 1.13 µm**

EN 2812-1
Resistance to particular washing agents (detergent A) **NO ALTERATION**

Dry residue **69 ± 1 %**

Walkability **6-10 h**

EN 2812-1
Resistance to particular washing agents (detergent B) **NO ALTERATION**

Brookfield ASTM D 2196
Viscosity **62.000 ± 2.500 mPas**

Access for traffic light **12 h**

EN 10792
Dirty grip **ΔL 0.32**

EN 11021
Odor release

Touch hardening at 20°C **4 h**

EN 1062-3
Capillary absorption **W < 0.1**

1.35 ± 0.05 kg/l

EN ISO 2813
Brilliance **80 - 90 Gloss**

Working temperature **-20 / +70 °C**

EN ISO 5470-1
Taber abrasion resistance expressed as weight loss in grams (H22 wheel - 1000 g - 1000 rpm) < **3.000 mg**

EN ISO 11998
Cleanability **ΔE 0.30**

Complete hardening at 20°C **7 day**

STORAGE AND CONSERVATION

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Protect from humidity.



WARNINGS AND PRECAUTIONS

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge. Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage. Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com.

It is forbidden to dispose of the product and/or packaging in the environment.

