

# Syntech Pavicrom Pool



**CUSTOMS CODE:** 3907 3000

**COMPONENTS:** Two-components

**APPEARANCE:** Liquid + Liquid

**AVAILABLE COLORS:** Request available colors

**PACKAGING AND DIMENSIONS:** Can 3.3 kg [A] - Can 6.7 kg [A] - Can 1.7 kg [B] - Can 3.3 kg [B] - Kit: 1 Can 3.3 kg [A] + 1 Can 1.7 kg [B] - Kit: 1 Can 6.7 kg [A] + 1 Can 3.3 kg [B]

## ALLOWED SUPPORTS

Concrete - Steel - Resin coatings





## APPLICATION METHODS

Paint roller - Sprayer


## TOOL CLEANING


Syntech Diluente Poliuretano

## KEY FEATURES

-  Density: 1.15 kg/l
-  Pot-life: 2 h
-  Temperature of use: +10 / +30 °C
-  UV-resistant

**A:B** Mixing ratio: 100:50 \_

 Shelf-life: 12 months

 Use wearing protective gloves



## TECHNICAL SPECIFICATIONS

*EN 1062-6*

Permeability to CO2 **Sd > 50 m**

*EN 1062-3*

Capillary absorption **w < 0.1**

*EN ISO 178*

Longitudinal elongation at break **10 %**

Complete hardening at 20°C **7 day**

Time before second coat at 20°C **12-72 h**

Touch hardening at 20°C **4-6 h**

*Persoz EN ISO 1522*

Hardness **220 s**

*EN ISO 2431*

Viscosity **40-100 s**

*EN 1542*

Adhesion by direct traction **≥ 2 MPa**

*EN ISO 7783-1*

Permeability to water vapor **Sd > 50 m**

*EN ISO 6272-1*

Impact resistance **Classe I: > 4 Nm**

Resistant to chemical agents

*EN ISO 2813*

Brilliance **≥ 80 Gloss**

## STORAGE AND CONSERVATION

Protect from freezing. Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Store the product at a temperature between +10°C and +30°C.

## WARNINGS AND PRECAUTIONS

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge. Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage. Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: [www.azichem.com](http://www.azichem.com). The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: [www.azichem.com](http://www.azichem.com).

It is forbidden to dispose of the product and/or packaging in the environment.

